

## SILICON IZ ENAMEL

**SILICON IZ ENAMEL** is a silicone resin enamel based on a combination of silicone resin, pigment and curing accelerator. It has the following characteristics.

1. It has excellent heat resistance. It withstands up to 450°C
2. It has excellent rust preventing and adhesion property in combination with GALBON S-HB
3. It has excellent weathering resistance.

### TECHNICAL DATA

Type	Silicone resin heat resisting paint				
Recommended Use	Boiler, Cylinder of engine, the inside of the exhaust pipe, Radiator Stove, Oil burner, steam pipe, etc.				
Colour	White , Black , Grey, As specified.				
Flash Point	27°C				
VOC	640 [g/litre]	EPA Method-24			
Solid by Volume	40.0 ± 2%				
Coverage (Theoretical)	0.06 - 0.09 l/m <sup>2</sup>	; 16.0 - 11.4 m <sup>2</sup> /l			
Wet Film Thickness	2.50 - 3.50 mils	; 63 - 88 microns			
Dry Film Thickness	1.00 - 1.40 mils	; 25 - 35 microns			
Drying Time	Temperature	10°C	20°C	30°C	40°C
(at D.F.T. 30 microns)	Surface Dry	50 mins.	30 mins.	20 mins.	10 mins.
	Hard Dry	5 hrs.	3 hrs.	1 hr.	30 mins.
Painting Interval	Minimum	12 hrs.	8 hrs.	5 hrs.	3 hrs.
(at D.F.T. 30 microns)	Maximum	-	-	-	-
Thinner	CMP-91				
Method of Application	Airless spray , Roller , Brush				
Conditions of Application	Temperature	Minimum 10°C			
	Humidity	Maximum 85% R.H.			
	For Airless spray :				
	Tip No.	GRACO 415			
	Paint output pressure	8.8 - 11.8 MPa.			
	Viscosity	25 - 30 sec (Ford Cup No.4 )			
	Thinning	0 - 15 % by volume			
Preceding coats	Galbon S-HB , Galbon S-HB 100 , Silicon Zinc Primer, etc.				
Subsequent coats					
Packaging	One pack product ; 3.785 Litres / Gallon , 18.925 Litres / Drum				
Shelf life at 25°C	In unopened container 12 months				

- Heating for 2 hours at 250°C is recommended for complete curing.
- Dry film thickness in excess of 40 microns per coat is not recommended to avoid blistering.

# ซิลิโคน ไอแซด อีนาเมล

ซิลิโคน ไอแซด อีนาเมล เป็นสีเคลือบเรซินซิลิโคน ผงสีชนิดทนความร้อน ซึ่งมีคุณสมบัติ ดังนี้

1. ทนทานต่อความร้อนได้ถึง 450 องศาเซลเซียส
2. ให้การป้องกันสนิมได้ดีเลิศเมื่อใช้ร่วมกับกัลบอน เอส-เอชบี (สีรองพื้นอินออกาเนค ซิงค์)
3. ให้การยึดเกาะที่เหนียวแน่นกับกัลบอน เอส-เอชบี
4. ทนทานต่อสภาวะอากาศ

## ข้อมูลทางเทคนิค

ชนิด	สีทนความร้อน ประเภทซิลิโคนเรซิน				
การใช้งาน	ใช้กับหม้อน้ำ ภายในท่อระบายความร้อน เต้าเผา ท่อไอน้ำเดือด เป็นต้น				
สี	ขาว , ดำ , เทา หรือตามที่ระบุ				
จุดวาบไฟ	27 องศาเซลเซียส				
ปริมาณสารอินทรีย์ระเหย	640 [กรัม/ลิตร]				
เนื้อสีโดยปริมาตร	40.0 ± 2%				
การปกคลุมพื้นผิวโดยทฤษฎี	0.06 - 0.09 ลิตร / ตร.ม.	16.0 - 11.4 ตร.ม. / ลิตร			
ความหนาฟิล์มเมื่อเปียก	2.50 - 3.50 มิล	63 - 88 ไมครอน			
ความหนาฟิล์มเมื่อแห้ง	1.00 - 1.40 มิล	25 - 35 ไมครอน			
ระยะเวลาแห้ง	อุณหภูมิ	10°C	20°C	30°C	40°C
ที่ความหนา 30 ไมครอน	แห้งผิว	50 นาที	30 นาที	20 นาที	10 นาที
	แห้งแข็ง	5 ชั่วโมง	3 ชั่วโมง	1 ชั่วโมง	30 นาที
ระยะเวลาแห้งก่อนทาสีทับ	อย่างน้อย	12 ชั่วโมง	8 ชั่วโมง	5 ชั่วโมง	3 ชั่วโมง
ที่ความหนา 30 ไมครอน	อย่างมาก	-	-	-	-
ทินเนอร์	CMP-91				
วิธีใช้งาน	เครื่องพ่นไร้อากาศ , แปรง				
ข้อเสนอแนะการปฏิบัติงาน	อุณหภูมิ	อย่างน้อย 10 องศาเซลเซียส			
	ความชื้นสัมพัทธ์	อย่างมาก 85%			
	สำหรับเครื่องพ่นไร้อากาศ				
	ขนาดหัวพ่นกราฟิโก	415			
	ความดันที่เครื่องพ่น	8.8 - 11.8 เมกาปาสกาล			
	ความหนืด	25 - 30 วินาที (ถ้วยฟอร์ต เบอร์ 4)			
การเจือจาง	0 - 15 % โดยปริมาตร				
สีชั้นก่อนทาสีนี้	กัลบอน เอส-เอชบี, กัลบอน เอส-เอชบี 100, ซิลิโคน ซิงค์ ไพร์เมอร์, อื่นตามที่ระบุในระบบสี				
ทาทับด้วยสี	-				
ประเภทการบรรจุ	สีส่วนเดียว ขนาดบรรจุ 3.785 ลิตร/แกลลอน , 18.925 ลิตร/ถัง				
อายุการเก็บที่ 25°C	12 เดือน ภายในภาชนะที่ไม่ถูกเปิด				

เพื่อให้ฟิล์มสีมีการแห้งตัวที่สมบูรณ์ แนะนำให้อบที่ 250°C นาน 2 ชั่วโมง

เพื่อหลีกเลี่ยงการเกิดปัญหาฟิล์มสี บวมพอง ไม่แนะนำให้ทำความหนาฟิล์มเมื่อแห้งเกิน 40 ไมครอนต่อชั้น